

TECHNICAL SPECIFICATIONS	BARDOLINE PRO S 125 HEXAGONAL
STANDARD	TS EN 544 4 X 2
WEIGHT OF THE FIBERGLASS	125 g/m ²
ADHESIVE STRIP	SELF - ADHESIVE
WIDTH	337 ±3 mm.
LENGTH	1000 ±3 mm
TENSILE STRENGTH (LONGITUDINAL)	800 N/5 cm (av.)
TENSILE STRENGTH (TRANSVERSAL)	600 N/5 cm (av.)
TEAR RESISTANCE (TRANSVERSAL)	150 N (av.)
WEIGHT	9 kg/m ²
BUNDLE NET COVERAGE AREA	3,45 m ²
PALETTE NET COVERAGE AREA	179,40 m ²
PACKING	PERFORATED, POLYETHYLENE COATED PACKAGES
SHEETS PER BUNDLE	24
BUNDLE PER PALETTE	52
BUNDLE WEIGHT	31,05 kg
PALLET WEIGHT	1614,60 kg
PALLET DIMENSION	cm 105 x 136 x 110 h

Application shall be carried out when the air temperature is 5°C or higher !