

TECHNICAL SPECIFICATIONS	BARDOLINE STANDARD
STANDARD	EN 544 4 X 2
WEIGHT OF THE FIBERGLASS	110 g/m ²
ADHESIVE STRIP	HOT - MELT ADHESIVE
WIDTH	336 ±3 mm
LENGTH	1000 ±3 mm
TENSILE STRENGTH (LONGITUDINAL)	600 / 850 N/5 cm (av.)
TENSILE STRENGTH (TRANSVERSAL)	600 / 700 N/5 cm (av.)
TEAR RESISTANCE (TRANSVERSAL)	100 / 130 N (av.)
WEIGHT	10,9 kg./m ²
BUNDLE NET COVERAGE AREA	3 m ²
PALETTE NET COVERAGE AREA	135 m ²
PACKING	MICROPERFORATED PE FOIL
SHEETS PER BUNDLE	21
BUNDLE PER PALETTE	45
BUNDLE WEIGHT	32,8 kg
PALLET WEIGHT	1496 kg
PALLET DIMENSION	cm 101 x 102 x 103 h (±3)

Application shall be carried out when the air temperature is 5°C or higher

