

<b>TECHNICAL SPECIFICATIONS</b>	<b>BARDOLINE TRADITIONAL</b>
<b>STANDARD</b>	EN 544 4 X 2
<b>WEIGHT OF THE FIBERGLASS</b>	110 g/m <sup>2</sup>
<b>ADHESIVE STRIP</b>	<b>HOT - MELT ADHESIVE</b>
<b>WIDTH</b>	336 ±3 mm
<b>LENGTH</b>	1000 ±3 mm
<b>TENSILE STRENGTH (LONGITUDINAL)</b>	600 / 850 N/5 cm (av.)
<b>TENSILE STRENGTH (TRANSVERSAL)</b>	600 / 700 N/5 cm (av.)
<b>TEAR RESISTANCE (TRANSVERSAL)</b>	100 / 130 N (av.)
<b>WEIGHT</b>	10,5 kg./m <sup>2</sup>
<b>BUNDLE NET COVERAGE AREA</b>	3 m <sup>2</sup>
<b>PALETTE NET COVERAGE AREA</b>	135 m <sup>2</sup>
<b>PACKING</b>	<b>MICROPERFORATED PE FOIL</b>
<b>SHEETS PER BUNDLE</b>	21
<b>BUNDLE PER PALETTE</b>	45
<b>BUNDLE WEIGHT</b>	31,50 kg
<b>PALLET WEIGHT</b>	1438 kg
<b>PALLET DIMENSION</b>	cm 101 x 102 x 100 h (±5)

Application shall be carried out when the air temperature is 5°C or higher

