

TECHNICAL SPECIFICATIONS	BILTMORE
STANDARD	EN 544 4 X 2
WEIGHT OF THE FIBERGLASS	90 g/m ²
WIDTH	349 mm (±3)
LENGTH	1038 mm (±3)
TENSILE STRENGTH (LONGITUDINAL)	700 N/5 cm (av.)
TENSILE STRENGTH (TRANSVERSAL)	600 N/5 cm (av.)
TEAR RESISTANCE (TRANSVERSAL)	130 N (av.)
WEIGHT	11,6 kg/m ² (±)
BUNDLE NET COVERAGE AREA	3,1 m ²
PALETTE NET COVERAGE AREA	139,5 m ²
PACKING	MICROPERFORATED PE FOIL
SHEETS PER BUNDLE	20
BUNDLE PER PALETTE	45 (139,5 m ²)
BUNDLE WEIGHT	35,96 kg
PALLET WEIGHT	1618,20 kg
PALLET DIMENSION	100 cm x 100 cm

Application shall be carried out when the air temperature is 5°C or higher !